

NITRO FLUX SOLDERING PASTE

FEATURES

- Smooth and creamy texture
- Lead-free
- Excellent wetting properties
- Promotes smooth flow of solder and reduced voids
- Ocleans while soldering, in all temperatures
- Ideal for lead-free brass
- REACH compliant
- RoHS compliant
- Meets ASTM B-813



Nitro Flux is a plumbing soldering paste flux, compatible with all lead-free and common soft solders. Nitro Flux is specifically designed for use on Copper, Brass, Tin and Lead.


APPLICATION

- Clean surfaces to be soldered and apply Nitro Flux
- Heat and apply solder without overheating, wipe clean once cooled
- Use AIM solders for best results

PROPERTIES

Parameter	Result
Color	Grayish silver
Viscosity	250 kcps ± 10%
Density	0.9711 ± 0.05
Melting Temperature	45°C (113°F)
Flash Point	182 - 230°C (359 - 446°F)
Auto Ignition Temperature	>300°C (>572°F)
Cold Temperature Usage	Performance not affected
Cold Temperature Viscosity	Ideal as low as 15°C (59°F)
	Spreadable as low as 4°C (39°F)





HANDLING & STORAGE

Parameter	Time	Temperature
Shelf Life	3 years	< 30°C (86°F)

Ideal storage temperature is room temperature, although Nitro Flux can be stored up to 35°C (95°F), and is still usable at 41°C (106°F). Do not mix used and unused paste flux in the same container. Reseal any opened containers.

AVAILABLE FORMATS

- **№** 57 g / 2 oz (#89261)
- **2**454 g / 1 lb (#89262)
- № 19.05 kg / 42 lb (#89263)

SAFETY

Use with adequate ventilation and proper personal protective equipment. Refer to the accompanying Safety Data Sheet for any specific emergency information. Do not dispose of any hazardous materials in non-approved containers.

Document Rev # NF5 Page 1 of 1

DISCLAIMER The information contained herein is based on data considered accurate and is offered at no charge. Product information is based upon the assumption of proper handling and operating conditions. Liability is expressly disclaimed for any loss or injury arising out of the use of this information or the use of any materials designated. Please refer to http://www.aimsolder.com/terms-conditions to review AIM's terms and conditions.